

# **Xianda Chemical Industrial Co. Ltd.**

Deheat Heat Insulating Roof Coating Manual

2016-05-17

# Instructions

1. Open the pail from the top.
2. Add appropriate amount of water, water to paint ratio 1:4 at most, water should not exceed 20% of the total weight of the mixture. Usually up to the line as shown in the red circle.



3. Stir the mixture to make it even.
4. Put the stirred mixture into container, prepare the spraying machine then apply.

# Precautions

1. Clean the surface before spraying, make sure there is no chunk of dust and dirt. A small amount of dust will not damage the effect.
2. Apply under the standard that one pail for 25 square meters, otherwise the performance will be damaged.
3. Mix the mixture evenly before applying.

# Frequently Asked Questions

1. Q: How to keep the paint after opened?  
A: When the paint is open, if not mixed with water, just put the head back and keep it still, if mixed with water, drop it after solidified.
2. Q: What to do if the paint is too sticky or partially solidified?  
A: If the paint is too sticky, or partially solidified, try again after dilution and filtration. if the mixture cannot be even, drop it.
3. Q: How to dispose the paint?  
A: Wait until it gets solidified. After solidified, the paint can be disposed as gravel, environmental-friendly. Do not dispose the paint in liquid into ground water, water course or sewage system.